

(A 01) Via Bresciani, 16 46040 Gazoldo degli Ippoliti Mantova Italy  
 Tel. +39 - 0376 685 1 www.marcegaglia.com

Stabilimento di Contino: Via Aido, 3, 46049 Volta Mantovana MN Tel. +39  
 0376 84601

#### CUSTOMER DATA AND DELIVERY

(A 06.1) CUSTOMER: **KROKAR D.O.O. (0000012339)** **Jesenice**  
 (A 06.2) CONSIGNEE: **KROKAR D.O.O. (0000012339)** **Jesenice**  
 (A 10) Delivery Number: **8930928142** (A 11) Shipping Notice: **1002003717** of **15/04/2026**

#### ORDER DATA

(A 08) Marcegaglia Order Number: **1195035628/000020**  
 (A 07) Customer Order Number: **00110**  
 (A 07) Date Of Order Confirmation To The Customer: **02/04/2026**

#### PRODUCT IDENTIFICATION

(B 01) Material Code: **55004051**  
 (B 09) Material Description: **TRT 70,00 -x6000 S355J2C TRAF**  
 (B 10) Material Description: **COLD DRAWN ROUND Toll h9 EN 10277**  
 (B 02) Steel Grade: **S355J2C S355D**  
 (B 03) Manufacturing Standard: **EN10277 ISO 683-7**  
 (B 14) Welding Technology:

#### SUPPLIED BATCH CHARACTERISTICS

ITEM	(B 07) BATCH NUMBER	(B 20) HEAT NUMBER	(B12) KG
1	26Q1504811	BM0234	944

#### CHEMICAL ANALYSIS

The chemical analysis refers to the raw material used. In accordance with EN 10204:2004 the values of the chemical analysis, unless otherwise specified, refer to the 3.1 type certificate of the raw material supplier.

ITEM	(B 07) BATCH NUMBER	(B 20) HEAT NUMBER	(C 71) C (%)	(C 72) Si (%)	(C 73) Mn (%)	(C 74) P (%)	(C 75) S (%)	(C 84) Al (%)	(C 83) Cu (%)
	MIN								
	MAX								
1	26Q1504811	BM0234	0.195	0.230	0.950	0.0100	0.0240	0.020	0.200

#### MECHANICAL PROPERTIES

ITEM	(B 07) BATCH NUMBER	TENSILE TEST (C 03) AT ROOM TEMPERATURE $t = (22 \pm 4)^\circ\text{C}$						(C 03) IMPACT TEST ON RAW MATERIAL, TEMPERATURE - 20 °			
		(C 01) SAMPLE POSITION	(C 02) SAMP. DIR.	(C 11) Rp 0.2 (MPa)	(C 11) Rm (MPa)	(C 12) Rm (MPa)	(C 13) A (%)	(C 42) KV1 (J)	(C 42) KV2 (J)	(C 42) KV3 (J)	(C 43) KVM (J)
		MIN	MAX								
1	26Q1504811	CAMP1	L	439	605	18.8	58	55	55	56	

Test Position: B=Coil Tail, C=Coil Centre, T=Coil Head  
 Test Direction: T=Transversal Sense, L=Longitudinal Sense

#### (D 94) NOTE

- WE CERTIFY THAT MATERIAL SUPPLIED COMPLIES WITH THE REQUIREMENTS AGREED ON ORDER  
 - MARCEGAGLIA IS CERTIFIED ACCORDING TO ISO 9001, ISO 14001, ISO14067, ISO 45001, ISO 50001 AND SA8000 STANDARDS, AS WELL AS OTHER SPECIFIC STANDARDS AND REGULATIONS.

IMPACT TEST ON RAW MATERIAL, TEMPERATURE -20°C

#### CERTIFICATE VALIDATION

(Z 02) The present test certificate is validated by **A. Dal Prato** - Quality Manager, Marcegaglia Specialties Volta Mantovana Plant authorized inspection representative, independent of the manufacturing department





**(A 02) INSPECTION CERTIFICATE 3.1 EN 10204**  
ACCORDING TO EN 10204:2004 ALPHANUMERIC CODES ACCORDING TO EN  
10168:2004  
(A 03) Certificate Number 10226252530  
(Z 02) Issue Date 15/04/2026

(Z 01) Statement of Compliance: WE CERTIFY THAT THE ABOVE MENTIONED  
PRODUCTS COMPLY WITH THE TERMS OF ORDER CONTRACT AND THE  
STANDARDS RECALLED IN THE PRESENT TEST CERTIFICATE