



SIDERMARCA

SIDERMARCA S.R.L.
Via della Libertà, 46
I-31050 Ponzano Veneto (TV)
Tel. +39 0422 96 30 69
Fax +39 0422 96 90 32

P.IVA e C.F. 110238004026/
R.E.A. TV 206888 | Cap. Soc. € 31.200 i.v.
info@sidermarca.com | sidermarca@legalmail.it | www.lucefin.com
Società assoggettata a direzione
e coordinamento da parte di Lucefin S.p.A.



| | | | | |
|-----------------|----------------------|------------------|-----------------|----------|
| A06 - Customer: | KROKAR D.O.O. | SPODNJI PLAVZ 28 | 4270 - JESENICE | SLOVENIA |
|-----------------|----------------------|------------------|-----------------|----------|

| | | |
|---|-----------------------|---------------------|
| A02 - Type of inspection document | A03 - Document number | Z02 - Date of issue |
| Values of the test report 2.2 according to EN 10204:2004 Manufacturer | CRL2617613676 | 27/05/2026 |

| |
|---|
| B02 - Grade - B03 - Execution - B01 - Section |
| S235JRC-S235B+C Cold Drawn Flat |

| | |
|--|------------------------|
| B02 - Standard of reference (edition in force at the date of the order) | EN ISO 683-7/24 |
|--|------------------------|

| | | | |
|-----------------|-----------------|--------------------------|----------------------|
| B09 - Size [mm] | B03 - Tolerance | B04 - Delivery condition | B05 - Heat treatment |
| 60 x 40 | h11 | +C | As rolled |

| | | |
|------------------------------------|-----------------|-------------------|
| A09 - Customer article designation | B08 - Quantity | B10 - Length [mm] |
| | [kg] 233 | 6190 |

| | | | |
|------------------|----------------|---------------------------|---|
| B07 - Lot | B07 - Heat | C70 - Stellmaking process | C93 - Reduction ratio of the hot rolled |
| L26003796 | 3124078 | | 13,50 |

| | | |
|------------------|------------------------|---------------------------------|
| A07 - Your Order | A08 - Our Confirmation | A10 - Transport document NR. |
| 260 | MRA2610440 | MRA2604444 of 27/05/2026 |

| HEAT ANALYSIS | | | | | | | | | | | |
|---------------|--------------|--------------|---------------|---------------|--------------|---------------|--------------|---------------|---------------|-------------|--|
| C71 | C72 | C73 | C74 | C75 | C76 | C77 | C78 | C79 | C92 | | |
| C % | Si % | Mn % | P % | S % | Cr % | Mo % | Ni % | Cu % | N % | CEV% | |
| 0,0890 | 0,184 | 0,622 | 0,0091 | 0,0090 | 0,097 | 0,0588 | 0,244 | 0,2731 | 0,0083 | 0,26 | |

Mechanical properties

Tensile test according to standard EN-ISO 6892

| | | |
|----------------|---------------------------|----------------|
| C12 - Rm [MPa] | C11 - Re-Rp 0,2 (*) [MPa] | C13 - A % 5d-L |
| 549,0 | 496,0 | 17,20 |

* According to the reference standard

HARDNESS ACCORDING TO STANDARD EN-ISO 6506-1

| | |
|----------|------------|
| C30 - HB | |
| C42 - | 166 |

Z01 - Remarks:

Il materiale non contiene prodotti di acciaio originari della Russia menzionati nell'Allegato XVII del Regolamento (UE) n. 833/2014 e sue ulteriori modifiche/
The material does not contain steel products originating in Russia mentioned in Annex XVII of Regulation (EU) No 833/2014 and its additional amendments.

The product supplied complies with the requirements of the order.

This product complies with the Directive 2011/65/EU RoHS II

This product complies with the Regulation (EC) n. 1907/2006 REACH

Material free from radioactive contamination

Country of production: Italy

A05 - Responsible for quality control

Luca Penato