



(A 02) INSPECTION CERTIFICATE 3.1 EN 10204
 ACCORDING TO EN 10204:2004 ALPHANUMERIC CODES ACCORDING TO EN 10168:2004
 (A 03) Certificate Number 10226414498
 (Z 02) Issue Date 23/06/2026

(A 01) Via Bresciani, 16 46040 Gazoldo degli Ippoliti Mantova Italy
 Tel. +39 - 0376 685 1 www.marcegaglia.com

Stabilimento di Contino: Via Aido, 3, 46049 Volta Mantovana MN Tel. +39 0376 84601

CUSTOMER DATA AND DELIVERY

(A 06.1) CUSTOMER: **KROKAR D.O.O. (0000012339)** **Jesenice**
 (A 06.2) CONSIGNEE: **KROKAR D.O.O. (0000012339)** **Jesenice**
 (A 10) Delivery Number: **8930977433** (A 11) Shipping Notice: **1002005879** of **23/06/2026**

ORDER DATA

(A 08) Marcegaglia Order Number: **1195059875/000020**
 (A 07) Customer Order Number: **00306**
 (A 07) Date Of Order Confirmation To The Customer: **12/06/2026**

PRODUCT IDENTIFICATION

(B 01) Material Code: **55002318**
 (B 09) Material Description: **TRT 28,00x3000 S355J2C TRAF**
 (B 10) Material Description: **COLD DRAWN ROUND Toll h9 EN 10277**
 (B 02) Steel Grade: **S355J2C S355D**
 (B 03) Manufacturing Standard: **EN10277 ISO 683-7**
 (B 14) Welding Technology:

SUPPLIED BATCH CHARACTERISTICS

ITEM	(B 07) BATCH NUMBER	(B 20) HEAT NUMBER	(B12) KG
1	26Q5508131	3122351	1045
2	26Q5508133	3122351	1046
3	26Q5508134	3122351	1047

CHEMICAL ANALYSIS

The chemical analysis refers to the raw material used. In accordance with EN 10204:2004 the values of the chemical analysis, unless otherwise specified, refer to the 3.1 type certificate of the raw material supplier.

ITEM	(B 07) BATCH NUMBER	(B 20) HEAT NUMBER	(C 71) C (%)	(C 72) Si (%)	(C 73) Mn (%)	(C 74) P (%)	(C 75) S (%)	(C 84) Al (%)	(C 83) Cu (%)
	MIN								
	MAX								
1	26Q5508131	3122351	0.155	0.237	1.291	0.0183	0.0240	0.020	0.111
2	26Q5508133	3122351	0.155	0.237	1.291	0.0183	0.0240	0.020	0.111
3	26Q5508134	3122351	0.155	0.237	1.291	0.0183	0.0240	0.020	0.111

MECHANICAL PROPERTIES

		TENSILE TEST (C 03) AT ROOM TEMPERATURE $t = (22 \pm 4)^{\circ}\text{C}$						(C 03) IMPACT TEST			
		(C 01) SAMPLE POSITION	(C 02) SAMP. DIR.	(C 11) Rp 0.2 (MPa)	(C 11) (MPa)	(C 12) Rm (MPa)	(C 13) A (%)	(C 42) KV1 (J)	(C 42) KV2 (J)	(C 42) KV3 (J)	(C 43) KVM (J)
		MIN									
		MAX									
ITEM	(B 07) BATCH NUMBER										
1	26Q5508131	CAMP1	L	555		669	15.2	50	47	53	50
2	26Q5508133	CAMP1	L	555		669	15.2	50	47	53	50
3	26Q5508134	CAMP1	L	555		669	15.2	50	47	53	50

Test Position: B=Coil Tail, C=Coil Centre, T=Coil Head
 Test Direction: T=Transversal Sense, L=Longitudinal Sense

(D 94) NOTE

- IMPACT TEST ON RAW MATERIAL, TEMPERATURE -20°C