



SIDERMARCA

SIDERMARCA S.R.L.

Via della Libertà, 46
I-31050 Ponzano Veneto (TV)
Tel. +39 0422 96 30 69
Fax +39 0422 96 90 32

P.IVA e C.F. 110238004026/

R.E.A. TV 206888 | Cap. Soc. € 31.200 i.v.

info@sidermarca.com | sidermarca@legalmail.it | www.lucefin.com

Società assoggettata a direzione
e coordinamento da parte di Lucefin S.p.A.



A06 - Customer:		KROKAR D.O.O.		SPODNJI PLAVZ 28		_ 4270 - JESENICE		_ SLOVENIA					
A02 - Type of inspection document						A03 - Document number		Z02 - Date of issue					
Values of the Certificate of Control 3.1 according to EN 10204:2004 Manufacturer						CRT2600011949		15/07/2026					
B02 - Grade - B03 - Execution - B01 - Section													
S355J2+AR Hot Rolled Round													
B02 - Standard of reference (edition in force at the date of the order)													
Scheda Tecnica S355J2_05													
B09 - Size [mm]		B03 - Tolerance		B04 - Delivery condition		B05 - Heat treatment							
140		EN 10060		+AR		As rolled							
A09 - Customer article designation			B08 - Quantity			B10 - Length [mm]							
			[kg] 764			6000/6500							
B07 - Lot		B07 - Heat		C70 - Stellmaking process									
L26018125		26/47938											
A07 - Your Order			A08 - Our Confirmation			A10 - Transport document NR.							
381			MRA2613326			MRA2605856 of 15/07/2026							
HEAT ANALYSIS													
C71	C72	C73	C74	C75	C76	C77	C78	C79	C80	C83	C90	C94	
C %	Si %	Mn %	P %	S %	Cr %	Mo %	Ni %	Cu %	Al %	V %	Nb %	Cr+Mo %	
0,1800	0,230	1,240	0,0160	0,0200	0,130	0,0200	0,090	0,1600	0,0230	0,0020	0,0010	0,1500	
CEV%	Cu+Cr+Mo+												
0,43	0,402												
Mechanical properties													
Tensile test according to standard EN-ISO 6892													
C12 - Rm [MPa]		C11 - Re-Rp 0,2 (*) [MPa]		C13 - A % 5d-L									
537,0		338,0		32,50									
* According to the reference standard													
Resilienza KV2 -20°C secondo la norma EN-ISO 148 / Impact test KV2 -20°C according to standard EN-ISO 148 / Kerbzähigkeit KV2 -20°C nach Standard EN-ISO 148 / Resilience KV2 -20°C Selon la norme EN-ISO 148													
KV2[J]	KV2[J]	KV2[J]											
49,0	54,0	61,0											
HARDNESS ACCORDING TO STANDARD EN-ISO 6506-1													
C30 - HB													
C42 -	155												

Z01 - Remarks:

The product supplied complies with the requirements of the order.

This product complies with the Directive 2011/65/EU RoHS II

This product complies with the Regulation (EC) n. 1907/2006 REACH

Material free from radioactive contamination

A05 - Responsible for quality control

Luca Perotto