



SIDERMARCA

SIDERMARCA S.R.L.

Via della Libertà, 46
I-31050 Ponzano Veneto (TV)
Tel. +39 0422 96 30 69
Fax +39 0422 96 90 32

P.IVA e C.F. 110238004026/

R.E.A. TV 206888 | Cap. Soc. € 31.200 i.v.

info@sidermarca.com | sidermarca@legalmail.it | www.lucefin.com

Società assoggettata a direzione
e coordinamento da parte di Lucefin S.p.A.



A06 - Customer:		KROKAR D.O.O.		SPODNJI PLAVZ 28		4270 - JESENICE		SLOVENIA							
A02 - Type of inspection document					A03 - Document number		Z02 - Date of issue								
Values of the Certificate of Control 3.1 according to EN 10204:2004 Manufacturer					CRT2600009016		06/10/2026								
B02 - Grade - B03 - Execution - B01 - Section															
42CrMo4+QT Hot Rolled Round															
B02 - Standard of reference (edition in force at the date of the order)															
EN ISO 683-2/18															
B09 - Size [mm]		B03 - Tolerance		B04 - Delivery condition		B05 - Heat treatment									
160		EN 10060		+QT		Quenching and Tempering									
A09 - Customer article designation			B08 - Quantity			B10 - Length [mm]									
			[kg] 484			3060									
B07 - Lot		B07 - Heat		C70 - Stellmaking process		C93 - Reduction ratio of the hot rolled									
L26015032		T10530/2026				6,60									
A07 - Your Order			A08 - Our Confirmation			A10 - Transport document NR.									
553			MRA2617159			MRA2607731 of 06/10/2026									
HEAT ANALYSIS															
C71	C72	C73	C74	C75	C76	C77	C79	C80							
C %	Si %	Mn %	P %	S %	Cr %	Mo %	Cu %	Al %							
0,4400	0,290	0,780	0,0120	0,0290	1,140	0,1980	0,0400	0,0250							
C50 - Jominy test H 1.5 mm															
mm	1,5	3	5	7	9	11	13	15	20	25	30	35	40	45	50
HRC	58,00	57,00	56,00	56,00	55,00	55,00	54,00	53,00	49,00	47,00	45,00	44,00	43,00	41,00	40,00
Mechanical properties															
Tensile test according to standard EN-ISO 6892															
C12 - Rm [MPa]				C11 - Re-Rp 0,2 (*) [MPa]				C13 - A % 5d-L				C14 - Z% L			
899,0				734,0				19,80				64,9			
* According to the reference standard															
Resilienza KV2 +20°C secondo la norma EN-ISO 148 / Impact test KV2 +20°C according to standard EN-ISO 148 / Kerzbähigkeit KV2 +20°C nach Standard EN-ISO 148 / Resilience KV2 +20°C Selon la norme EN-ISO 148															
KV2[J]		KV2[J]		KV2[J]											
96,0		102,0		93,0											
HARDNESS ACCORDING TO STANDARD EN-ISO 6506-1															
C30 - HB															
C42 - 272															
Grain Size (ASTM E112) 8,00															
- Materiale controllato ad ultrasuoni cl.3 EN 10308															
Z01 - Remarks:															
The product supplied complies with the requirements of the order.															
This product complies with the Directive 2002/95/EC RoHS as amended															
This product complies with the Regulation (EC) n. 1907/2006 REACH															
Material free from radioactive contamination															

A05 - Responsible for quality control

Luca Penato